



STYLE
4901 / 4903

WEAVING
EXCELLENCE
WITH
INNOVATION



Code	Color	SOLAR OPTICAL PROPERTIES				SHGC/G VALUE g-tot (glass & blind)	
		TS	RS	AS	TV	SINGLE 1/4 CL	INSULATING 1 HA
STYLE 4901 - 1%							
P06	Chalk	9	83	8	7	0.18	0.17
P25	Chalk/Black - face	1	22	77	1	0.50	0.32
P25	Chalk/Black - back	1	54	45	1	0.33	0.24
P26	Chalk/Wheat - face	6	65	29	6	0.28	0.22
P26	Chalk/Wheat - back	6	75	19	6	0.22	0.19
Q07	Kettal Grey - face	3	48	49	3	0.37	0.26
Q07	Kettal Grey - back	3	37	60	3	0.43	0.29
Q16	Tobacco - face	2	8	90	2	0.58	0.36
Q16	Tobacco - back	2	6	92	2	0.59	0.37
Q22	Flaxen - face	3	42	55	3	0.40	0.27
Q22	Flaxen - back	3	57	40	3	0.31	0.23
Q23	Whitesands - face	7	65	28	6	0.28	0.22
Q23	Whitesands - back	7	67	26	6	0.27	0.21
Q25	Birch - face	5	57	38	4	0.32	0.23
Q25	Birch - back	5	64	31	4	0.28	0.22
Q26	Cobblestone - face	3	36	61	4	0.43	0.29
Q26	Cobblestone - back	3	55	42	4	0.33	0.24
Q27	Soft Grey	5	58	37	4	0.31	0.23
V03	Pewter/Chalk - face	3	56	41	4	0.32	0.23
V03	Pewter/Chalk - back	3	30	67	4	0.46	0.30
V10	Ebony	1	5	94	1	0.59	0.36
V28	Slate - face	2	11	87	3	0.57	0.36
V28	Slate - back	2	8	90	3	0.58	0.36
STYLE 4903 - 3%							
P06	Chalk	11	81	8	10	0.19	0.17
P25	Chalk/Black - face	3	25	72	3	0.49	0.32
P25	Chalk/Black - back	3	56	41	3	0.32	0.23
P26	Chalk/Wheat - face	9	65	26	9	0.28	0.22
P26	Chalk/Wheat - back	9	73	18	9	0.23	0.19
Q07	Kettal Grey - face	4	47	49	5	0.37	0.26
Q07	Kettal Grey - back	4	37	59	5	0.43	0.29
Q16	Tobacco - face	3	8	89	4	0.58	0.37
Q16	Tobacco - back	3	6	91	4	0.59	0.37
Q22	Flaxen - face	6	43	51	7	0.40	0.27
Q22	Flaxen - back	6	57	37	7	0.32	0.23
Q23	Whitesands - face	9	63	28	8	0.30	0.23
Q23	Whitesands - back	9	67	24	8	0.27	0.21
Q25	Birch - face	7	56	37	7	0.25	0.24
Q25	Birch - back	7	63	30	7	0.29	0.22
Q26	Cobblestone - face	4	38	58	4	0.43	0.29
Q26	Cobblestone - back	4	56	40	4	0.32	0.23
Q27	Soft Grey	8	57	35	8	0.32	0.23
V03	Pewter/Chalk - face	4	53	43	5	0.34	0.24
V03	Pewter/Chalk - back	4	29	67	5	0.47	0.30
V10	Ebony	3	5	92	5	0.60	0.37
V28	Slate - face	3	12	85	4	0.55	0.35
V28	Slate - back	3	8	89	4	0.58	0.37



Microban® antimicrobial protection inhibits the growth of stain-causing bacteria, mold and mildew on the shade.



PRODUCT CERTIFIED FOR LOW CHEMICAL EMISSIONS
UL.COM/GG
UL 2818



MIF Seal of Approval



TS = Solar Transmittance
RS = Solar Reflectance
AS = Solar Absorption
TV = Visual Transmittance

SHGC = Solar Heat Gain Coefficient

1/4 CL = 1/4" Clear Glass
1 HA = 1" Heat Absorbing Glass

Fabrics Installed Internally
Zero-Degree Profile Angle

For additional performance values, test references and technical definitions visit us at www.phifer.com.

STYLE 4901 / 4903 SPECIFICATIONS

Form follows function in this unique combination of color and weave. Using thin and light weight vinyl-coated polyester yarns, Styles 4901 and 4903 are as versatile as they are beautiful. Styles 4901 and 4903 can also be used in exterior shading systems.

FIRE CLASSIFICATION	California U.S. Title 19 (small scale) NFPA 101 (Class A Rating) BS 5867 2008 Part 2 Type B Performance CAN/ULC-S 109-03 (large and small scale) CAN/CGSB2-4.162-M80	NFPA 701-2004 TM#1 (small scale) IBC Section 903.1 (Class A Rating) NFPA 701 TM#2 (large scale) ASTM E 84 (Class 1)	
BACTERIA AND FUNGAL RESISTANCE	ASTM E 2180 GREENGUARD Mold and Bacteria Standard includes Microban antimicrobial additives	ASTM G21 ASTM 6329	AATCC30 Part 3 ASTM D 3273
ENVIRONMENTAL CERTIFICATION	GREENGUARD Certified to these standards for low chemical emissions into indoor air during product usage	GREENGUARD Gold	
LEAD FREE	RoHS/Directive 2002/95/EC ANSI/WCMA A 100.1-2007 for lead content US Consumer Product Safety Commission Section 101		REACH (EC 1907/2006) compliant
WARRANTY	10-year interior	5-year exterior	
ACOUSTICAL PERFORMANCE	NRC (Noise Reduction Coefficient) and SAA (Sound Absorption Average) tested in accordance with ASTM C423-09a		
UV PROTECTION	Seal of Approval by the Melanoma International Foundation (MIF) for effectiveness in preventing sun damage to the skin or eyes		

STYLE	4901	4903
WIDTHS	63" and 98" 160.0 cm and 248.9 cm	63" and 98" 160.0 cm and 248.9 cm
ROLL LENGTH	30 Linear Yards 27.4 m	30 Linear Yards 27.4 m
COMPOSITION	17% Polyester 83% Vinyl on Polyester	17% Polyester 83% Vinyl on Polyester
MESH WEIGHT	16.2 oz/yd ² 549.27 g/m ²	14.9 oz/yd ² 505.20 g/m ²
FABRIC THICKNESS	0.028 in 0.71 mm	0.027 in 0.69 mm
OPENNESS FACTOR	Approximately 1%	Approximately 3%
UV BLOCKAGE	Approximately 99%	Approximately 97%
ACOUSTICAL VALUE	NRC .60 / SAA .59	NRC .25 / SAA .25